
Effects: sanded metallic, brushed metal appearance

Products required:

- PU Isolating filler DP 491-9343
- Sanded metallic DB 46777-M0 (colour tone)
- UNA-PUR 55x(gloss level)

Please observe the precise addition of hardeners and thinners in the information below.

Description/features:

Creating effects similar to brushed metal.

Areas of use:

Unusual, creative accents for exclusive interiors, furniture, kitchens, etc.

Sample process:

Accents in interiors in brushed steel:

- Substrate material: milled, laminated chipboard or MDF board, treated with filler and milled
- Prime with one coat of 150 - 200 g/m² PU Isolating filler DP 491-9343
mixing ratio (by volume) 4 :1 with PU Hardener DR 405
if necessary with the addition of 10 % thinner DV 490
- Dry for at least 16 hours at 20 °C
- Sand according to the effect desired with grain 80 - 180 in one direction
- Apply a top coat of 80 to 120 g/m² of PU Sanded metallic DB 46777-M0790 silver, applying from both sides along the sanding direction,
mixing ratio of 10 : 1 with PU Hardener DR 470
if necessary with the addition of 5 – 10 % Thinner DV 490
- optionally apply a top coat of
either UNA-PUR DE 559 glossy or DE 554 semi-matt after a maximum of 2 hours, without sanding between coats
mixing ratio of 10 : 1 with PU Hardener DR 470
- Dry for at least 16 hours at room temperature 20°C

Information on use and safety:

Please observe the latest technical information and safety data sheets for the individual products listed.

Special instructions:

The effect depends on the selected effect sanding and the application quantity of metallic paint. Polyurethane lacquers should not be used or dried at product or room temperatures below 18°C.

In order to avoid adhesion problems, polyurethane lacquered surfaces should be freshly sanded before applying the top coating.

Effects: sanded metallic, brushed metal appearance

Please apply a test coat under real conditions!

Note:

This information is for advice and is based on the best knowledge available and careful research in line with current state of the art practice. This information cannot be held as legally binding. We also refer you to our terms and conditions of business.

The Material Safety Data Sheet according to the regulation (EC) No. 1907/2006 is available.